


19X7 Non-Rotating

Size (in)	Approx. Wt per ft (lbs)	Nominal Breaking Load (lbs)	
		IPS	EIPS
1/4	0.11	5,020	5,540
5/16	0.18	7,800	8,600
3/8	0.22	11,180	12,300
7/16	0.26	15,160	16,600
1/2	0.45	19,700	21,600
9/16	0.58	24,800	27,200
5/8	0.71	30,600	33,600
3/4	1.02	43,600	48,000
7/8	1.39	59,000	65,000
1	1.82	76,600	84,400
1-1/8	2.30	96,400	106,200
1-1/4	2.84	118,400	130,200


35X7 Rotation Resistant

Size (in)	Approx. Wt per ft (lbs)	Nominal Breaking Load (lbs)	
		1960 Grade	2160 Grade
3/8	0.28	14,920	16,440
7/16	0.38	20,200	22,400
1/2	0.49	27,200	29,200
9/16	0.62	34,600	37,000
5/8	0.77	43,400	45,600
3/4	1.11	61,800	65,800
7/8	1.51	83,200	89,400
1	1.97	108,800	116,800
1-1/8	2.50	137,800	147,800
1-1/4	3.08	172,000	182,600
1-3/8	3.73	212,000	220,000
1-1/2	4.44	240,000	262,000



7X7X7 Galvanized Cablelaid

Size (in)	Approx. Weight (lbs/ft)	Nominal Breaking Load (lbs)		
		Grade A	Grade B	Grade C
5/16	0.135	6,490	7,080	7,670
3/8	0.195	9,350	10,200	11,100
7/16	0.273	12,900	14,100	15,200
1/2	0.346	16,400	17,900	19,400
9/16	0.446	21,100	23,000	24,900
5/8	0.558	26,500	28,900	31,300
3/4	0.786	37,300	40,700	44,100
7/8	1.093	51,800	56,500	61,200
1	1.405	66,600	72,600	78,700



7X7X19 Galvanized Cablelaid

Size (in)	Approx Weight (lbs/ft)	Breaking Load (lbs)		
		Grade A	Grade B	Grade C
3/8	0.195	9,100	9,900	10,800
7/16	0.270	12,700	13,900	15,000
1/2	0.341	16,100	17,600	19,100
9/16	0.440	20,700	22,600	24,500
5/8	0.550	26,000	28,400	30,700
3/4	0.776	36,600	39,900	43,300
7/8	1.079	50,700	55,300	59,900
1	1.387	65,300	71,200	77,200